

POM Regrind A

	MFR	比重 Specific Gravity	引張破壊強さ Tensile Strength	引張破壊伸び Tensile Elongation(Break)	曲げ強さ Flexural Strength	曲げ弾性率 Flexural Modulus	アイゾッド衝撃強さ(ノッチ付き) Notched Izod Impact	荷重たわみ温度 Deflection temperature under load
Test method	ASTM D1231 343°C 1.2kgf	ASTM D792	ASTM D638	ASTM D638	ASTM D638	ASTM D790	ASTM D256	ASTM D648
Unit	g / 10 min	-	Mpa	%	Mpa	Mpa	J/m	°C
	29	1.41	60	15		2400		168
For reference Asahikasei Delrin DE20279	30	1.41	63	20		2800		170

